

Dentifrice Protection Against Dentin Demineralization in an In Vitro Study

A.K. Burwell and D.C. Greenspan
NovaMin Technology, Inc, Alachua, Florida, USA



International Association of Dental Research

IADR Abstract

Originally Presented at
85th General Session
March 2007, New Orleans USA
Abstract # 1764

Objective: When applied directly to the tooth surface or incorporated into a dentifrice, NovaMin® relieves hypersensitivity by occluding dentinal tubules through the formation of an acid-resistant apatite layer. This work evaluates the ability of two calcium phosphate-containing materials to protect dentin from demineralization during a 10-day *in vitro* remineralization/demineralization (remin/demin) study.

Methods: Bovine tooth roots were ground, polished, and acid-etched to expose the dentin layer and create an *in vitro* hypersensitivity model. Randomly-selected samples were left untreated and represent “sound” dentin. The remaining samples were subjected to a 10-day remin/demin cycle that consisted of a twice-daily 30-minute soak in demineralizing solution (pH=4.52) at 37°C followed by a two-minute brushing with either NovaMin®-containing SootheRx™, RECALDENT™-containing MI Paste, or DI water. Samples were soaked in artificial saliva (pH=7.00) at 37°C between the two daily demineralization/brushing periods. Samples treated with only DI water are referred to as “demineralized” dentin. Knoop hardness (KH) was measured on all dentin surfaces using a load of 50 grams for 15 seconds. Results were analyzed using ANOVA and Holm-Sidak tests ($p < 0.01$).

Results: All data are mean±S.E.M. with $n=15$. Demineralized dentin had a KH (50.85 ± 0.85) that was significantly lower than sound dentin (65.43 ± 0.50 , $p < 0.001$). The KH of dentin treated with NovaMin® during the remin/demin cycle (79.75 ± 1.10 , $p < 0.001$) was significantly greater than sound and demineralized dentin. Dentin treated with RECALDENT™ had a KH (52.12 ± 1.27) that was significantly lower than sound dentin ($p < 0.001$) and did not differ from demineralized dentin ($p = 0.358$).

Conclusion: Current microhardness data indicate that treatment with a NovaMin®-containing dentifrice creates a tenacious surface layer that protects dentin from demineralization caused by repeated acid challenges. Within the limitations of this model, however, the same protection was not provided by amorphous RECALDENT™. These results further explain the observed reductions in clinical hypersensitivity following treatment with a NovaMin®-containing dentifrice.

Key Words: Hypersensitivity, Remineralization, Demineralization, Dentin, Microhardness

J Dent Res 86(Spec Iss A):1764, 2007 (www.dentalresearch.org).




Figure 1: Dentinal Microhardness Before and After 10-day Study